

CERAMIC LAMINATE

Background InformationField Of The Invention

The present invention relates to a ceramic laminate according to
5 the definition of the species in Claim 1 having at least one solid
electrolyte layer.

Background Information

Such a ceramic laminate is used as a heating device in sensor
elements for electrochemical sensors, such as for lambda probes
10 for measuring the oxygen concentration in the exhaust gas of
internal combustion engines, or as a temperature sensor for
determining the temperature of a medium, especially the exhaust
gas of internal combustion engines. The layer buildup is obtained,
for instance, by foil casting, silk-screening, laminating and
15 sintering.

In one known sensor element for a lambda probe described in
published German patent document (DE 198 34 276 A1), altogether
three solid electrolyte layers are present, and the resistor track
with its two lead tracks is embedded between two insulating layers
20 which each cover one solid electrolyte layer, a sealing frame being
applied all around the insulating layers, which is made of the same
material as the solid electrolyte layers. Whereas the lower solid
electrolyte layer is used as the substrate, on which the lower
insulating layer lies, a reference gas channel is recessed into
25 the solid electrolyte layer that covers the upper insulating layer.
Onto this solid electrolyte layer, the third solid electrolyte
layer is set, which on its upper side carries an outer measuring
electrode or Nernst electrode covered by a protective layer, and
on its lower side carries an inner measuring electrode or reference
30 electrode in the vicinity of the reference gas channel. The solid
electrolyte layers include essentially zirconium oxide (ZrO_2), and

the insulating layers include aluminum oxide (Al_2O_3). After the application of the layers, ~~such as e.g.~~, using the silk-screening method or by laminating of cast foils, the sensor element is sintered at a temperature such as 1300 - 1600°.

5 As a result of different thermal coefficients of expansion of the materials used for the solid electrolyte layers and the insulating layers, after a stress-free state has set in during sintering, compressive stresses are created during cooling of the sensor element, on the inside of the insulating layers. The resistor track
10 embedded in the insulating layers also lies free in an insulating channel that forms in the insulating layers, since the thermal coefficient of expansion of the material of the resistor track, just as the thermal coefficient of expansion of the material of the solid electrolyte layers, is greater than the thermal
15 coefficient of expansion of the material of the insulating layers. At sufficiently slow cooling rate, the stress-free state prevailing at the sintering temperature is still maintained down to a temperature that is far below the sintering temperature, the so-called inversion temperature. The compressive stresses then set
20 in upon further cooling. If the inversion temperature is exceeded in the operation of a sensor element, the stress relationships reverse, and the insulating layers now experience tensile stress because the solid electrolyte layer and the resistor track expand more greatly. Because of these tensile stresses, cracks occur in
25 the insulating layers, which spread out transversely to the longitudinal direction of the insulating layers, and lead to the destruction of the sensor element as soon as they cut through the insulating layers and the solid electrolyte layers, and exhaust gas enters into the reference gas channel. Because of the low
30 critical tensile stress of the material of the insulating layers, even small tensile stresses may ~~act to~~ trigger cracks.

In order to increase the service life of the sensor elements, ~~in the known sensor element,~~ pore-forming materials are

conventionally added to the aluminum oxide-containing material of the insulating layers, before sintering. By this deliberate introduction of a porosity into the material of the insulating layers, the elasticity of the insulating layers is increased, and
5 the compressive and tensile stresses are reduced thereby. However, the reduction in material stresses occurs mainly on the inside of the insulating layers, and the reduction decreases with an approach
~~tetowards~~ towards the boundary surfaces of the insulating layers, since in this location an open surface is present into which the cracks
10 are well able to enter. Such boundary surfaces appear particularly in the direction towards the resistor track, where the material of the insulating layers has formed the insulating channel filled by the resistor track.

In one known temperature sensor for determining the temperature
15 of a medium, particularly e.g., the exhaust gas of internal combustion engines, as described in published German patent document (DE 100 45 940 A1), the laminate has a substrate made of a ceramic oxide material, such as yttrium-stabilized zirconium oxide, two insulating layers made, for instance, of aluminum oxide
20 which enclose between them the electrical resistor track having two electrical lead tracks, and of which the one is applied to the substrate, and a cover layer that covers the other insulating layer that faces away from the substrate, that is made of the same material as the substrate. The resistor track is developed in a
25 meandering shape, while the two lead tracks run parallel to each other. The resistor track which forms the measuring range of the temperature sensor has a greater electrical resistance than the two lead tracks. This is attained by a variation of the material composition in the resistor track, on the one hand, and in the lead
30 tracks, on the other hand. All the tracks are made of platinum pastes, which contain platinum and aluminum oxide as well as a binder. Because of different percentage proportions of platinum and aluminum oxide, the specific Ohmic resistance of the material

is manipulated for the resistor track and the lead track. The resistor track and the lead tracks are produced by printing of the platinum paste onto the one insulating layer.

~~Summary of the Invention~~Summary

5 The ceramic laminate according to the present invention, ~~having~~
~~the features of Claim 1,~~ has the advantage that, because of the
great width of the resistor track, the ~~maximizing~~maximum width of
which is only limited by the width of the laminate, the
~~inclinations~~susceptibility of the insulation to form cracks is
10 clearly reduced. This is conditioned, on the one hand, by the wider
resistor track giving off heat to the insulation over a greater
surface, and therefore being less overheated in response to rapid
heating. On the other hand, in the wide resistor track, defects
created by silk-screening lead much less rapidly to narrow spots
15 in the resistor track than in the case of a narrow resistor track.
Because of that, no local hot spots, or at least substantially fewer
hot spots, occur, which trigger the cracking mechanism described
at the outset. If, for example, the width of the resistor track
is made to be greater than 500 μm , the ratio to the lateral
20 fluctuations of the silk-screening is less than 5%. Because of that,
the resistor fluctuations which trigger the hot spots are less than
5%. In addition, fluctuations in the track thickness of the
resistor track created by height fluctuations in the insulating
layer average out better, because of the greater width of the
25 resistor track, since the ratio of width to cross section of the
resistor track is rather high, according to the present invention,
for instance, greater than 1/14 μm . Because of the differently
sized specific Ohmic resistance of the materials used for the lead
track, on the one hand, and the resistor track, on the other hand,
30 for instance, platinum or platinum alloys having different
proportions of aluminum oxide or alloy components, the resistance
ratio between the resistor track and the lead tracks is held in

a favorable manner with regard to the concentration of the heating performance in the resistor track.

~~The measures specified in the further claims permit advantageous further developments and improvements of the laminate indicated in Claim 1.~~

According to one advantageous ~~specific~~example embodiment of the present invention, the specific Ohmic resistance of the material of the resistor track is selected to be at least twice as great as the specific Ohmic resistance of the material of the lead tracks. In this context, ~~preferably~~ the temperature coefficient of the material of the resistor track is less than the temperature coefficient of the material of the lead tracks.

According to one advantageous ~~specific~~example embodiment of the present invention, the width of the resistor track is greater than that of a lead track, ~~preferably~~e.g., the width of the resistor track being 50% greater than the width of a lead track.

According to another ~~preferred~~~~specific~~example embodiment of the present invention, the insulation in which the resistor track is embedded is made of a first insulating layer applied to the one solid electrolyte layer, on which at least the resistor track is printed, and a second insulating layer that covers at least the resistor track. ~~Preferably, the~~The two insulating layers may also cover the circuit board conductors. The insulating layers are ~~preferably~~may be made of aluminum oxide (Al_2O_3).

~~Brief Description of the Drawings~~

~~The present invention is explained in greater detail in the following description on the basis of exemplary embodiments shown in the drawings. The figures show:~~

Brief Description of the Drawings

Fig. 1 shows a cross-section of a sensor element for a $\lambda=1$ probe, taken along the line I - I shown in Figure 2.

Fig. 2 shows a longitudinal section of the sensor element according to, taken along line II - II shown in Figure 1.

Figs. 3 and 4 ~~in each case the same illustration as in Figure 2,~~
according to show longitudinal sections of additional exemplary
5 embodiments of the sensor element according to the present
invention.

~~Description of the Exemplary Embodiments~~ Detailed Description

The sensor element, shown in cross-section in Figure 1, for a voltage-jump sensor or a $\lambda=1$ sensor for measuring the oxygen
10 concentration in the exhaust gas of internal combustion engines, has a laminate 10, whose individual layers, lying one over the other, are made by sealing layer processes, such as foil casting and/or by silk-screening. A lower first solid electrolyte layer 11 is used as substrate for the construction of laminate 10, while an upper
15 second solid electrolyte layer 12, on its upper side, carries an outer measuring electrode or Nernst electrode 14, and on its lower side, carries an inner measuring electrode or reference electrode 15. An electrical heater 16 is situated on first solid electrolyte layer 11, and between electrical heater 16 and second solid
20 electrolyte layer 12 lies a third solid electrolyte layer 13, in which a reference gas channel 17 is recessed, in the region of reference electrode 15, which is in contact with a reference gas, preferably e.g., air. Nernst electrode 14 is covered by a porous protective layer 18 that coats the surface of second solid
25 electrolyte 12. All solid electrolyte ~~layer~~ layers 11 through 13 are made of yttrium-stabilized zirconium oxide (ZrO_2).

Electric heater 16 includes an electrical resistor track 20 embedded in an insulation, and two lead tracks 24 and 25 to resistor track 20. The insulation is made of a lower insulating layer 21
30 which lies on first solid electrolyte layer 11 and an upper insulating layer 22 which lies against solid electrolyte layer 13. Insulating layers 21, 22 are made essentially of aluminum oxide

(Al₂O₃), and may contain additives. Both insulating layers 21, 22 are fastened to the respectively assigned solid electrolyte layer 11 and 13 ~~respectively~~, for instance, by a foil adhesive or by being printed on. The two insulating layers 21, 22 are surrounded by a sealing frame 23, which is made of zirconium oxide, just as are solid electrolyte layers 11 - 13.

As may be recognized from the sectional representation according to Figure 2, resistor track 20 is connected in one piece to the two circuit board conductors 24, 25 that run parallel to each other, which are also embedded in the two insulating layers 21, 22. Each printed circuit conductor 24, 25 is contacted at its end facing away from electrical resistor track 20 to a contact surface printed onto the free surface of first solid electrolyte layer 11, passing through first solid electrolyte layer 11. Via the two contact surfaces, electrical resistor track 20 is able to be connected to a current source, such as the vehicle electrical system. Electrical resistor track 20, just as circuit board conductors 24, 25 and the contact surfaces having through-hole plating, are made of platinum or a platinum cermet. After the production of laminate 10, it is sintered at a temperature of ~~ea-~~approximately 1300 - 1600°C and cooled thereafter.

The aluminum oxide of insulating layers 21, 22, the zirconium oxide, ~~surrounding insulating layers 21, 22,~~ of solid electrolyte layer 11, 13 (surrounding insulating layers 21, 22) and of sealing frame 23, and the platinum of electrical resistor track 20, have quite different thermal coefficients of expansion, the thermal coefficients of expansion of the zirconium oxide and of the platinum being greater than the thermal coefficient of expansion of the aluminum oxide. During sintering, a stress-free state sets in, ~~which is present~~results in response to sufficiently slow cooling ~~even~~ down to a certain temperature below the sintering temperature. Upon further cooling below the so-called inversion temperature, compressive stresses are created on the inside of

insulating layers 21, 22. If the sensor element is rapidly heated beyond the inversion temperature during operation, the stress ratios in laminate 10 reverse, so that the aluminum oxide of insulating layers 21, 22 is now subjected to a tensile stress by the zirconium and the platinum. The maximum tensile stress component, in this context, is greatest along the longitudinal extension of laminate 10. Because of the tensile stresses, cracks form in the aluminum oxide, which spread perpendicular to the greatest tensile stress, that is, in the transverse plane of laminate 10, and may lead to the destruction of the ~~function of the sensor element.~~

In order to minimize the danger of triggering cracks, the following measures are taken in accordance with the present invention:

In a first printing step, the two lead tracks 24, 25 are printed onto insulating layer 21, using a material having a small specific Ohmic resistance. For this, a platinum paste ~~using~~containing an aluminum oxide ~~supporting framesupport~~, e.g., of 5%, is used. In the second printing step, resistor track 20 is printed onto lower insulating layer 21 in a meandering shape, using a material having a substantially greater specific Ohmic resistance. The specific Ohmic resistance of the material for resistor track 20 is selected, in this instance, to be at least twice as great as that of the material for lead tracks 24, 25, and the temperature coefficient of the material of resistor track 20 is less than that of the material of lead tracks 24, 25. Here too, a platinum paste is used which, however, ~~has~~contains an aluminum ~~supporting framesupport~~ of, for example, 30%. In this context, resistor track 20 obtains quite a great width, which is selected to be as big as possible with respect to the available width of insulating layer 21. The width of resistor track 20 is greater than the width of lead tracks 24, 25, and is selected to be at least 50% greater. For example, the width of resistor track 20 is dimensioned at 560 μm , ~~preferably~~or around 1000 μm .

In the exemplary embodiment of Figure 2, resistor track 20 is printed onto lower insulating layer 21 in three meandering windings, having altogether four parallel meander legs 201 - 204. The inner meander legs 202, 203, that face each other each have a local
5 widening in their track widths. The thickness in which resistor track 20 and lead tracks 24, 25 are printed on ~~is preferably~~may be equal and is selected at less than 14 μm , for example. In this context, the minimum thickness of resistor track 20 is specified at ~~ea-~~approximately 5 μm because of the cohesion of the platinum
10 grains. The maximum width of the resistor track 20 is limited by the width which is specified by lower insulating layer 21, and in addition, interstices between meander legs 201 - 204 ~~having~~have to be taken into consideration. These interstices are also minimized.

15 Because of the extreme width of resistor track 20, defects in resistor track 20, which are created by the printing of resistor track 20, in contrast to narrow resistor tracks, do not lead to narrow spots, which effect local overheating as a result of their great resistance, and thereby trigger the above-described crack
20 mechanism in insulating layers 21, 22 made of aluminum oxide. Also, because of the great width of resistor track 20, the ratio of width to cross section is rather large, e.g., in the ~~named~~above exemplary embodiment it is greater than 1/14 μm , so that fluctuations in the thickness of resistor track 20 extensively average out, based on
25 height fluctuations of lower insulating layer 21, because of the great width of resistor track 20.

In the exemplary embodiment of Figure 3, an extremely wide resistor track 20 is printed onto lower insulating layer 21. In the platinum
30 paste for resistor track 20, extremely fine platinum grains are used, having a grain diameter of 200 nm to 1 μm . Such fine-grained platinum is called nanoplatinum. The nanoplatinum is applied in a scanty filled paste, having a proportion of 50%, and after the

removal of the binder, the extremely thin resistor track 20 is obtained at a track thickness of less than 5 μm .

In the exemplary embodiment of Figure 4, the three meandering windings of resistor track 20 are printed having the four meander legs 201 - 204 as a net. Because of this, the number of edges that are ~~submitted~~subjected to spread in the silk-screening is substantially increased, and the resistance fluctuations over the course of resistor track 20 largely average out. Overall, there is created a resistor track 20 having an almost constant resistance over the length of the track, and local resistance fluctuations, which lead to hot spots, are eliminated.

The laminate according to the present invention, having resistor track 20 embedded in an insulation, is not only suitable as an electric heater for a $\lambda=1$ probe or a broadband lambda probe. It may also be applied as a temperature sensor, such as for measuring the temperature of the exhaust gas of internal combustion engines. ~~A temperature sensor of this kind is described in DE 100 45 940 A1.~~ In this case a cover layer is additionally printed onto upper insulating layer 22, which may be made of the same material as first solid electrolyte layer 11. Alternatively, one may do without this cover layer, and upper insulating layer 22 may be sintered in a gas-tight manner.

In one modification of the laminate, in which resistor track 20 and lead tracks 24, 25 are made of platinum and solid electrolyte layers 11, 12 are made of a zirconium oxide in which only a fraction of the current flows in the platinum, one may do without the embedding of lead tracks 24, 25 in an electrical insulation.

~~Abstract~~

ABSTRACT

A ceramic laminate is ~~described~~provided which has at least one solid electrolyte layer—~~(11)~~, an electrical resistor track—~~(20)~~ embedded in an insulation, and especially running in a meandering shape, and two electrical lead tracks ~~(24, 25)~~ to the resistor track ~~(20)~~. To reduce the danger of crack formation in the insulation, the resistor track ~~(20)~~ is made up of a material having a greater specific Ohmic resistance compared to the material of the lead tracks—~~(24, 25)~~ and has as great a track width as possible at a low track thickness.

~~(Figure 2)~~

15